JELUTONG

Dyera costulata

WOOD DESCRIPTION

Color:	*Light yellow*
Sapwood:	*Not Demarcated*
Texture:	*Fine*
Grain:	*Straight*

CHARACTERISTICS

- Easy to work
- Durable
- Resistant to termites

COMMON USES

- Cabinetwork
- Blockboard
- Furniture and Furniture components
- Sliced veneer
- Paneling (interior)
- Joinery (interior)
- Boxes and crates
- Wood carving

AVAILABILITY

- Select & Better
- Mixed Grain
- 5/4, 6/4, 8/4, 12/4 Thicknesses

PHYSICAL / MECHANICAL PROPERTIES

Air Dry Density	*2.3 lbs/bf*	Fiber Saturation Point:	*%*
Specific Gravity:	*0.45*	Crushing Strength:	*3,916 lbf*
Janka Hardness (lbs):	*390*	Static Bending Strength:	*1,956,269 lbf*
Volumetric Shrinkage:	*6.2%*	Modulus of Elasticity:	*1,456,179 lbf*
Total Tangential Shrinkage (TS):	*5.5%*	Stability:	*Stable*
Total Radial Shrinkage (RS):	*2.3%*		
TS/RS Ratio:	*2.4*		

WORKING PROPERTIES

Blunting Effect:	*Normal*	Slicing:	*Good*
Sawteeth Recommended:	*Ordinary or alloy steel*	Nailing / screwing:	*Good*
Cutting Tools:	*Ordinary*	Gluing:	*Good*
Peeling:	*Good*		

All Rights Reserved